AD 742416

# FOREIGN TECHNOLOGY DIVISION

THIS IS AN UNEDITED ROUGH DRAFT TRANSLATION BY
JOINT PUBLICATIONS RESEARCH SERVICES

TRUE STRUCTURE OF MOLYBDENUM AND TUNGSTEN
SINGLE CRYSTALS GROWN FROM THE GAS PHASE

by

W. Reitzenstein, G. Weise

Approved for public release;
Distribution unlimited.

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author)	2a. REPORT SECURITY CLASSIFICATION
Foreign Technology Division Air Force Systems Command U. S. Air Force.	UNCLASSIFIED
	2b. GROUP

3. REPORT TITLE

TRUE STRUCTURE OF MOLYBDENUM AND TUNGSTEN SINGLE CRYSTALS GROWN FROM THE GAS PHASE

4. DESCRIPTIVE NOTES (Type of report and inclusive dates)

Translation

5. AUTHOR(S) (First name, middle initial, last name)

Reitzenstein, W. ; Weise, G.

6. REPORT DATE	7a. TOTAL NO. OF PAGES	7b. NO. OF REFS
1971	19	13

8a. CONTRACT OR GRANT NO.	9a. ORIGINATOR'S REPORT NUMBER(S)
b. PROJECT NO. 7343	
c.	FTD-HC-23-1787-71
d.	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)

10. DISTRIBUTION STATEMENT

Approved for public release; distribution unlimited.

11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY
	Foreign Technology Division Wright-Patterson AFB, Ohio

13. ABSTRACT

It is shown that the morphol. and crystal perfection of single crystals of Mo and W obtained by vapor deposition using the thermal decompn. of halides, depends on the supersat. the crystals were exam. by metallog. investi- gations and X-rays to det. position, extension, and kind of the disturbances. At lower supersatns. with a given equil. form face, distrubances appears regularly in layers and within defined crystallog. positions, which depend on the growth direction in different planes. In most cases the disturbed layer appears in the mirror plane of the planes contg. The growth steps. [AP:107866]

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Molybdenum Alloy						
Tungsten Alloy						
Metal Single Crystal						
Metal Vapor Deposition						
Metallograpny						
Crystallograpny						
Refractory Metal						
X-Ray Technology						
Thermal Decomposition						
Chemical Decomposition						
Halide						

UNEDITED ROUGH DRAFT TRANSLATION

by Joint Publications Research Services

TRUE STRUCTURE OF MOLYBDENUM AND TUNGSTEN SINGLE CRYSTALS GROWN FROM THE GAS PHASE

Author: W. Reitzenstein, G. Weise

English pages: 19

systems[8] investigated, and with speed of precipitation, if
several reactions are neglected which participate in the
reaction system. In order to obtain single crystals free of
disorders, growth conditions have to be set up which make
possible growth by way of two dimensional nucleus formation,
or at steps formed by screw dislocations. The load charge
and habitus of the equilibrium form planes appearing under
these conditions during growth from the gas phase are depen-
dent on the supersaturation. Thus, they determine the macro-
and microscopic morphology of the single crystals which, in a
certain way, is also predetermined by the rod axis orientation
of the support. The morphological findings can be classified
as follows:

    1) Shell or boundary planes which are either
      a) smooth growing equilibrium form planes and shift
      parallel in the direction of the normal, or
      b) coarse planes whose subindividuals are made up
      from equilibrium form planes
    2) Surface profiles on the shell planes with crystallo-
      graphically defined boundaries which are called steps.

There is a close connection between the morphology and
the true structure of such crystals in dependence on super-
saturation; it can be classified as follows:

1) Growth with little supersaturation on macroscopi-
cally and microscopically stepped smooth, and particularly
coarsened planes will lead to an inhomogeneous crystal volume.
The inhomogeneities characteristic of this growth are desig-
nated as disorder areas and layers, and show an extent in the
form of sequential dislocation arrangements which is compar-
able to the build-up of subgrain boundaries up to cracks as
coarse disorders in the same crystallographic directions.

2) Growth with higher supersaturation over macroscopi-
cally smooth surfaces, especially if all shell planes are
equilibrium form planes, will result in a homogeneous (free
of disorder areas and layers) crystal volume from molybdenum[7]
made by thermal decomposition homogeneous single crystals
with rod axis orientations of $\langle 110 \rangle$, $\langle 100 \rangle$ and $\langle 111 \rangle$
could be obtained which are bound by the equilibrium form
planes $\{110\}, \{100\}, \{211\}, \{111\}$ depending on the
orientation of the rod axis. Tungsten[8] grown according

-3-

to the same procedure shows {110} exclusively as equili-
brium form plane under favorable growth conditions, so that
only ⟨111⟩ will lead to exclusive limitation by smooth
{110} planes and thus to homogeneous single crystals.
It is the goal of this paper to characterize more closely the
fine structure of these single crystals with metallographic
and x-ray methods. The coarse structure at cracks and sub-
grain boundaries can be made visible by optical microscopy
where polished {100} planes[9] also permit proof of dis-
locations with the help of etch pits, as well as by the Berg-
Barrett technique[10] ;its advantages as against the micro-
scopical procedure were pointed out by Gunther.[11] Under
the conditions of the particularly clear arrangement of dis-
order layers built up from dislocation sequences in crystals
grown from the gas phase, the Berg-Barrett technique (BB) is
at the limit of resolution. The orientation differences of
such growth layers were obtained through rocking curves and
topographical recordings made with a double-crystal spectro-
meter (DCS)[12] From the contrast variations of different
crystal sections, the DCS method also gives qualitative infor-
mation on the kind and the preferred type of dislocations in
the disorder layers. Of all x-ray topographical procedures
the Lang method[13] offers the most favorable resolution
conditions, however, it requires the most expensive sample
preparation. The Lang method supplies information on the
density, the kind and type of dislocations.

Presently, no theoretical statements are available on
the formation of coarse disorders like cracks or even dislo-
cations in crystals grown from the gas phase so that the
results on the true structure were only organized according
to phenomenology.

2. True Structure of Molybdenum and Tungsten Single Crystals.

2.1 Inhomogeneous Single Crystals.

2.1.1 Interaction of Morphology and True Structure.

To characterize single crystals grown from the gas
phase over macroscopically stepped shell planes, the desig-
nations growth region, - layer and disorder region layer
will be used. Growth regions are the crystal volumes grown

-3-

radially into the various crystallographic directions which are bound at the surface by shell planes. The growth layers are positioned in the growth regions and are the crystal volumes which are bound at the surface by the profile of the steps on the shell planes. Disorder regions are the transition regions between growth regions and disorder layers are the boundary planes of growth layers.

Fig. 1 shows a schematic of the growth and disorder orientations for a $\langle 110 \rangle$ single crystal. Growth areas extend into $\langle 211 \rangle$ and $\langle 110 \rangle$ directions, also, $\langle 100 \rangle$ and $\langle 111 \rangle$ regions may occur depending on the growth conditions. The disorder regions and disorder layers appear at the following places in the order of their extent:

a) disorder regions between colliding growth regions,
b) disorder layers as a trace of the hollow edges of steps on coarsened planes,
c) disorder layers as trace of the hollow edges on smooth planes.

Furthermore, the extent of these disorders decreases with increasing supersaturation. This is caused by a reduced supersaturation in the border region of the shell plane and in the hollow edges of the steps. This shows up as a sensitive characteristic of supersaturation at the morphological appearances of the step formation. This supersaturation gradient towards the border region of the macroscopic shell planes, as represented schematically in Fig. 2, is larger than in the profile of the steps of convex and enclosed edge (Fig. 2). Thus, from the standpoint of the supersaturation gradient the extent of the disorders is larger in the disorder regions than in the disorder layers. The flatter the surface relief of the steps is developed on the shell planes the smaller is the supersaturation gradient and with it the degree of disorder.

A few examples will demonstrate the dependence on supersaturation of these disorders. Low supersaturations with macro steps on the shell planes (Fig. 3) lead to cracks in the disorder regions and layers (Fig. 3b). Due to bigger subindividuals the disorder region between the $\langle 211 \rangle$ growth regions shows more pronounced cracks than that between $\langle 211 \rangle - \langle 110 \rangle$.

-4-

Fig. 1. Schematic representation of the growth and disorder regions as well as growth and disorder layers for a ⟨110⟩ single crystal. a) disorder regions between colliding ⟨211⟩ and ⟨110⟩ growth regions. Depending on the degree of supersaturation between the ⟨211⟩ regions there will also be a ⟨100⟩ growth region. b) Disorder layers as trace of the hollow edges of steps on coarse planes. c) Disorder layers as trace of the hollow edges on smooth planes.

The crack shaped disorder layers in the growth regions clearly can be associated with the traces of the hollow edges of the steps. The interval of the steps on the surface correlates with the distances of the cracks in the crystal volume. Relatively higher supersaturations lead to micro steps on the shell planes and to disorder layers in the growth regions which exhibit dislocation sequences in the typical arrangement of the subgrain boundaries as is shown by the (010) polished cross sections of a ⟨110⟩ tungsten single crystal.

The expansion of the disorders to a three dimensional

crack can be seen clearly in the {100} growth region in Fig. 4. It is caused by larger subindividuals with increasing layer thickness. The possibility in principle of a disorder free growth is pointed out by the undisturbed initial layer. The crystallographic location and the build-up of the disorder layers which are well visible on the higher light optical micrographs of Fig. 4b are discussed taking the ⟨110⟩ tungsten single crystal shown in Fig. 4 as an example.

2.1.2 Crystallographic location and build-up of the disorder layers.

Since only plane orientations around (100) can be etched metallographically an investigation of several crystal sections was carried out through combination with the x-ray DCS method. The goal was to determine the crystallographic position of the disorder layers caused by the surface profile and the degree of reciprocal angles of the growth layers which for larger orientation differences can be seen in the splitting of Laue reflexes.

The following results were obtained:

a) The mirror symmetry plane or the bisecting line of the angle of the planes of the growth steps on the shell planes result as the crystallographic location of the disorder layers between the growth layers. Thus, the following disorder layers (Fig. 5) appear for single crystals with ⟨110⟩ rod axis orientation in the growth regions of the corresponding shell planes.

Shell planes {110}:

Growth region (Ī10):
Growth steps: (Ī10), (011): disorder layer: (101);
Growth steps: (Ī10), (01Ī): disorder layer: (10Ī).

Growth region (1Ī0):
Growth steps: (1Ī0), (0Ī1) disorder layer: (Ī01);
Growth steps: (1Ī0), (0ĪĪ): disorder layer: (Ī0Ī).

Fig. 2. Schematic representation of the supersaturation gradient above the snell planes (a) and above the macro steps (b).

In the metallographic (101) section (Fig. 4b) these disorder layers run obliquely in {110} directions, in the (100) section horizontally in the direction {100}.

If the crystallographic axis is identical with the rod axis then on each {110} snell plane all four {110} growth steps will appear which lead to a total of four effective {110} disorder layers.

Snell planes {211}:

Growth steps: {110} with the zone axes [1̄1̄1]
(111);
Disorder layer (110).

Fig. 3. <110> Molybdenum single crystals with low
supersaturation. (a) (110) Shell plane with (110)
macro steps. (b) Crack shaped disorder regions and
layers in the crystal volume.

In the metallographic (010) cut (Fig. 4a,c) the dis-
order layer is perpendicular in the direction {001}.

Shell planes {100}:

Growth steps: (011), (101), (0$\bar{1}$1), ($\bar{1}$01);
Disorder layer: {110} with zone axis [001];
Disorder layer: {100} with zone axis [001].

In the metallographic (010) section (Fig. 4a) the disorder layers
are parallel to (001). Fig. 6 shows the various locations in the (001)
section.

The extent of the disorders in the crystals depends on the height
difference in the surface relief. The degree of disorder continues to be
the result of the number of effective disorder layers. This number is
highest in the {100} shell plane region so that this region is disturbed
the most. In the disorder region {110} {211} the disorder layers of the
neighboring growth regions (Fig. 3b) penetrate each other and lower super-
saturations lead to the formation of cracks.

(b) In order to determine the kind and type of dislocation

Fig. 4: Subgrain boundaries as disorder layers in a (010) polished cross section of a ⟨110⟩ tungsten whisker crystal. (a) Survey photographs... (b) ... tion of the subgrain boundaries in the ⟨111⟩ region, 100×. (c) Position of the subgrain boundaries in the ⟨100⟩ and ⟨211⟩ region, 100×.

- 9 -

(211) shell planes   (110) shell planes
   o   growth steps   o   growth steps
   x   disorder layer   x   disorder layer

arrangement of the disorder
layers in the region of the
(110)   - shell planes

Fig. 5: Schematic representation of the location of
the disorder layers in (110) single crystals.

In the disorder layers the orientation and extinction x-ray
contrast on (001), (1$\bar{1}$2), (1$\bar{1}$1) and (110) sections were com‑
pared. The experimental findings showed that the {110}
disorder layers between growth layers are built up from
dislocations with a predominant share of steps. Qualitative‑
ly, the contrasts can be associated with dislocations of the
type b = 1/2 [1$\bar{1}\bar{1}$] and b = 1/2 [1$\bar{1}$1] (Fig. 7).

Fig. 6: (001) layer with {110} and {100} disorder layers in the (001) growth region.


Fig. 7: Location of the possible step dislocations in the disorder layer. (a) Representation in stereographic projection, (b) in the (110) disorder layer of the {111} growth regions, (c) in the {110} disorder layers of the {110} growth regions.

The {100} disorder layers appearing in the {100} growth region ought to be built up from step dislocations only.

(c) From the distance of the rows of etch figures the width of the growth layers turns out to be about 50 µm. This corresponds to the distances of the fine-stripes on the x-ray films (Fig. 8a) which, therefore, can be associated with the

-11 -

growth layers.

(d) From the distance of the etch figures in the disorder layers $D \leq 5 \mu m$ the reciprocal angles between the growth layers is $\overline{\theta} \leq 0.2$ angle minutes with the simplified assumption of $\theta = b/D$. In agreement with this it was found that the orientation differences determined with x-rays are of the order of magnitude of 1 angle minute. It can be seen from the rocking curves of large crystal regions with about 100 growth layers that these reciprocal angles do not add up in the same sense of rotation to a correspondingly high orientation width but obviously occur with alternating direction of rotation. This can be explained with a change of the sign (+,-) of the dislocations in the neighboring disorder layers.

(e) The substrates for the manufacture of single crystals, made through recrystallization after critical deformation, have a subgrain structure which continues in the material growing on them in the form of "growth regions" of different orientation. These growth regions (designated B) are causing the coarse picture structuring in Fig. 8 with reciprocal angles of several minutes. Based on the appearance of contrast at various oriented sections it is assumed that the disordered transition layers between the growth regions consist mainly of screw dislocations with b = 1/2 [11$\bar{1}$].

(f) The DCS picture of the ($\bar{1}$10) shell plane (Fig. 9) shows a cell structure within the growth layers. It results from the combined appearance of (011), (01$\bar{1}$) growth steps and with this, also growth layers of (10$\bar{1}$) and (10$\bar{1}$). The partial pictures (recorded with one minute difference each in the angle of incidence make clear the reciprocal angles between the cells which is due to an accumulation of predominately step dislocations.

2.2   Homogeneous single crystals.

A homogeneous crystal volume is formed by growth over macroscopically smooth shell planes as is shown in Fig. 10 for a ⟨100⟩ molybdenum single crystal with four each {110} and {100} shell planes. The following can be said about the true structure:

(110)

$\Delta \vartheta = 1'$

Fig. 8: DCS picture of an inhomogeneous tungsten
single crystal. (1$\bar{1}\bar{1}$) section through (211) growth
regions. The stripe-shaped partial pictures are ob-
tained by stepwise change of the angle of incidence.
The fine-stripes can be attributed to the growth layers
or (110) disorder layers, respectively and the coarse
picture structuring to the growth regions.

(a) No phase boundary can be noticed between the sub-
strate and the layer grown on it. The regions only differ
by density of dislocations.

(b) In the layer grown on the substrate subgrain
boundaries may be present. The causes for this could be:

[1] accidental supersaturation inhomogeneities in
the growth conditions;

-13 -

Fig. 9: DCS picture of the (110) shell plane of an inhomogeneous tungsten single crystal. The cell structure is formed by (101) and (101) disorder layers intersecting each other.

[2] impurities on the surface of the substrate;

[3] subgrain boundaries present in the substrate continue into the layer growing on it as can be shown metallographically, and on BB pictures (Fig. 11a,b). Zone molten rods used as substrates always exhibit such subgrain boundaries while single crystalline filaments made through recrystallization after critical deformation largely are free of these disorders (Fig. 11c).

(c) The layer deposited from the gas phase shows low disorder densities which have been caused by the following methodic advantages:

[1] small temperature gradient, and, thus, avoidance of thermal stresses:

[2] high thermal purity of the halides as base material this includes decreased solubility of the components of the remaining gas atmosphere;

[3] low void concentration with low deposition temperatures.

The pictures of the sections were enlarged with an optical microscope, they have low resolution and show an

Fig. 10: ⟨100⟩ molybdenum single crystal with high
supersaturation: (a) macroscopically smooth surface,
(b) homogeneous crystal volume.

irregular distribution of the dislocations. The Lang tech-
nique, however, provides data on the density, kind and type
of the dislocations. Topographies of various {110} reflexes
were made of a ⟨100⟩ molybdenum single crystal free of
subgrain boundaries. The pictures (Fig. 12) yield the
following results:

(a) in the growth regions of the shell planes of {110}
and {100} the crystal shows contrasts from dislocation
groups and single dislocations. Contrast appearances due
to anomalous transmission point can lead to a dislocation
density of 10^4 cm/cm^3.

(b) Geometry of the dislocation arrangement, the con-
trasts and the possible Burgers vectors point to step
dislocations of the type $b = 1/2$ ⟨111⟩ .

(c) The contrasts in the {110} and {100} growth re...
are positioned parallel to ⟨110⟩ directions. These dislo-
cations shown in the picture with $b = 1/2$ ⟨111⟩ and $\sigma =$
⟨211⟩ among the planes possible with ⟨211⟩ as zone axis
are probably located in {110} planes, analogous to the
importance of {100} as growth and disorder planes for th...

- 15 -

Fig. 11: Influence of the true structure of the substrate on the layer growing on it. (a) {100} cross-section of a ⟨110⟩ molybdenum single crystal with subgrain boundaries from the zone molten substrate. (b) proof of such subgrain boundaries with BB pictures. (c) BB picture of a single crystal free of subgrain boundaries with single crystalline substrate made through recrystallization.

Fig. 12:   Lang pictures of dislocation structures in the (001) section of a molybdenum single crystal: (a) topography with ($\bar{1}$10) reflex; (b) topography witn($\bar{1}\bar{1}$0) reflex.

innomogeneous crystals. In the {100} growth region a pre-ferred direction of the contrasts towards ⟨310⟩   to ⟨210⟩ can be found. These dislocations are built up from partial pieces with step character which also ought to be located in {110} planes.

3. Summary

The morphology of single crystals grown from the gas phase is a result of the combination of equilibrium form planes. Low supersaturations lead over stepped, microscopically smooth planes, and especially coarsened planes, to an inhomogeneous crystal volume. With higher supersaturations growth takes place over macroscopically smooth planes and results in homogeneous single crystals with a low dislocation density ($<10^4$ cm^{-2}) free of disorder regions and layers. Disorders in the inhomogeneous crystals are arranged in layers whose crystallographic location is determined by morphology. It was found that the disorder layer is always the plane of mirror symmetry of the planes of neighboring growth steps. Therefore, the preferential position of the {110} equilibrium form plane and the {110} steps on smooth and coarsened shell planes resulting from it, lead predominantly to {110} disorder layers. The disorder layers contain mainly dislocations with step character of the type b = 1/2 $\langle 111 \rangle$ which cause alternating tilting in the order of magnitude of one angle minute between neighboring growth layers. Larger orientation differences in the single crystals are due to disorders in the substrate which continue into the volume growing on it.

BIBLIOGRAPHY

1. A. E. Van Arkel, Reine Metalle, Springer, Berlin, 1939
2. H. Schaefer, Chemische Transportrealctioner (Chemical Transport Reactions), Verlag Chemie Weinheim, 1962
3. I. N. Stranski and R. Kaischew, Z. Physik. Chem. Vol B26, pp 100, 114, 312, 1934.
4. F. C. Frank, in "Growth and Perfection of Crystals", Ed. R. H. Doremus et al, Wiley, New York, 1958, p 441.
5. A. A. Tschernov, Kristollografiya (Crystallography), Vol 7, p 895, 1962; Vol 8 p 87, 1963.
6. G. Weise, Kristall and Technik, Vol 2, No. 3, p 339, 1967.
7. G. Weise and R. Guenther, J. Crystal Growth, Vol 6, p 167, 1969-1970

8. G. Weise and R. Owsian, J. Less-Common Metal, Vol 20, p 99, 1970
9. P. Finke, Prakt, Metallog. Vol 2, No 4, p 151, 1965
10 H. Wadewitz, Reinststoffprobleme in Wessenschaft und Technik, Vol 3, Ed. E. Rexer, Akademie-Verlag, Berlin, 1967, p 301
11. F. Guenther, Freiberger Forschungsh., Vol B141, Metallkunde 1969, p 161.
12. W. Reitzenstein, Dissertation, DAW, Berlin, 1971
13. C. Becker, Dissertation, DAW, Berlin, 1970

- END -

TD-…-…-…7-…